

Physical Properties			
Grade	T.S.	Y.S.	% Age Elongation of
	Mpa	Mpa	MIN
	MIN	MIN	
Fe 330	330	195	20
Fe 410	410	235	18

These are preferred OD & Thickness. Other sizes not included may be supplied as specified by purchaser.