

Mechanical Properties		
	Grade A	Grade B
Yield Strength	205 Mpa(Min)	240Mpa(Min)
Tensile Strength	330 Mpa(Min)	415Mpa(Min)
Elongation%	As per ASTM A-53, Table *4.1, 4.2	